

KING HY-PACT®

Tolerance information:

Gauges 1/8" through 1" ± 5% | Length and width plus only at room temperature

Custom sheet sizes, gauges and colors available

Properties	Units	ASTM	Nominal Values
Density	g/cc	D1505	0.95
Tensile Strength @ Yield	p.s.i.	D638	>4,100
Elongation @ Yield	%	D638	9.6
Flexural Modulus	p.s.i.	D790	186,000
Durometer	Shore D	D2240	65
Izod Impact	ft.lbs./in. ²	D256	16.6
Brittleness Temp.	°C (°F)	D746	<-90°C (<-130°F)
Vicat Softening Temp.	°C (°F)	D1525	130°C (266°F)
Heat Deflection Temp. 66 p.s.i.	°C (°F)	D648	75°C (167°F)
Coefficient of Linear Expansion	in/in/F°	D696	6.0 x 10 ⁻⁵
Miller Number/SAR Results	SAR	G75	3209
Taber	Index	D4060	5

QUV Accelerated Weathering Tester	King StarBoard® UV Protected		King Hy-Pact® UV Protected		UHMW UV Protected		ASTM
	Unexposed	2,000 hours of exposure	Unexposed	2,000 hours of exposure	Unexposed	2,000 hours of exposure	
Tensile @ Yield 70°F (psi)	4,260	4,250	4,100	4,100	3,010	2,970	D638
Elongation @ Yield 70°F (%)	9.2	9.1	9.6	9.6	16	3.2	D638
Tensile @ Break 70°F (psi)	690	680	1,930	1,440	No Break	2,940	D638
Elongation @ Break 70°F (%)	160	155	260%	210%	No Break	3.4%	D638
Taber Index	21	45	5	12	2	182	D4060
IZOD notch 70°F (ft lbs/sq in)	4.1	3.9	16.6	15.7	20.02	0.84	D256
Coefficient of Friction - Kinetic	0.0888	0.0888	0.107	0.107	0.129	0.129	D1894
Coefficient of Friction - Static	0.0832	0.0832	0.102	0.102	0.102	0.102	D1894
Miller Number/SAR Results	8643.3	---	3209.0	---	453.9	---	

All values are determined on specimens prepared according to ASTM Standards.
King HY-PACT® is made entirely from FDA approved materials.

King Hy-Pact® is NSF approved for Standard 51.

King Plastic Corporation Limit of Warranty is your money refunded or defective material replaced. All statements, information and data given herein are believed to be accurate and reliable. It is presented without guaranty, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated or that other measures may not be required.

