

**IAPD THERMOPLASTICS RECTANGLE**
**Polyetheretherketone (PEEK)**
**SEMI-CRYSTALLINE HIGH  
PERFORMANCE THERMOPLASTICS**
**TYPICAL PROPERTIES OF POLYETHERETHERKETONE (PEEK)**

ASTM or UL Test	Property	Unreinforced	Glass Reinforced		30% Carbon Reinforced
			20%	30%	
<b>PHYSICAL</b>					
D792	<b>Specific gravity</b>	1.32	1.43	1.49	1.44
D792	<b>Specific volume (in<sup>3</sup>/lb)</b>	21.0	19.3	18.6	—
D570	<b>Water absorption, 24 h, 1/8-in thk (%)</b>	0.5	—	0.11	0.06
<b>MECHANICAL</b>					
D638	<b>Tensile strength (psi)</b>	13,300	17,800	22,800	30,200
D638	<b>Elongation (%)</b>	50	2.5	2.2	1.3
D638	<b>Tensile modulus (10<sup>5</sup> psi)</b>				
	At 302°F	1.6	—	—	—
	At 356°F	0.58	—	—	—
D790	<b>Flexural strength (psi)</b>	24,700	27,800	33,800	46,100
D790	<b>Flexural modulus (10<sup>5</sup> psi)</b>	5.3	9.7	15	18.9
D256	<b>Impact strength, Izod (ft-lb/in of notch)</b>	1.6	1.6	1.8	1.6
<b>THERMAL</b>					
C177	<b>Thermal conductivity (10<sup>-4</sup> cal-cm/sec-cm<sup>2</sup>°C)</b>	6.0	—	10.4	22.1
D696	<b>Coefficient of thermal expansion (10<sup>-5</sup> in/in-°C)</b>				
	<150°C	4.7	2.4	2.2	1.5
	>150°C	10.8	—	—	—
D648	<b>Deflection temperature (°F)</b>				
	At 264 psi	320	545	600	600
UL 94	<b>Flammability rating, 1/8 in</b>	V-0	V-0	V-0	V-0
	<b>Max. Service Temperature, Long Term</b>	428°F-500°F	—	500°F	500°F
<b>ELECTRICAL</b>					
D150	<b>Dielectric constant</b>				
	At 1 kHz	3.3	—	—	—
D150	<b>Dissipation factor</b>				
	At 1 kHz	0.003	—	—	—
D257	<b>Volume resistivity (ohm-cm)</b>				
	At 73°F, 50% RH	4.9x10 <sup>16</sup>	—	—	1.4x10 <sup>5</sup>

TYPICAL PROPERTIES OF POLYETHERETHERKETONE (PEEK)					
ISO or UL Test	Property	Unreinforced	Glass Reinforced 20%	30%	30% Carbon Reinforced
PHYSICAL					
ISO1183	<b>Specific gravity</b>	1.32	1.43	1.49	1.44
ISO1183	<b>Specific volume (cm<sup>3</sup>/g)</b>	0.756	0.695	0.669	—
ISO62	<b>Water absorption, 24 h, 3.1mm thk (%)</b>	0.5	—	0.11	0.06
MECHANICAL					
ISO178	<b>Tensile strength (MPa)</b>	91.70	122.73	157.20	208.22
ISO527	<b>Elongation (%)</b>	50	2.5	2.2	1.3
ISO527	<b>Tensile modulus (10<sup>3</sup> MPa)</b>				
	At 150°C	1.10	—	—	—
	At 180°C	0.39	—	—	—
ISO178	<b>Flexural strength (MPa)</b>	170	191	233	317
ISO178	<b>Flexural modulus (10<sup>3</sup> MPa)</b>	3.65	6.68	10.34	13.03
ISO180	<b>Notched izod impact strength (J/m)</b>	85	85	96	85
THERMAL					
ASTM C177	<b>Thermal conductivity (10<sup>-4</sup> cal-cm/sec-cm<sup>2</sup>-°C)</b>	6.0	—	10.4	22.1
ISO11359	<b>Coefficient of thermal expansion (10<sup>-5</sup> in/in-°C)</b>				
	<150°C	0.84	0.43	0.39	0.27
	>150°C	1.94	—	—	—
ISO75	<b>Deflection temperature (°C)</b>				
	At 1.80 MPa	160	280	316	316
UL 94	<b>Flammability rating, 1/8 in</b>	V-0	V-0	V-0	V-0
ELECTRICAL					
IEC250	<b>Dielectric constant</b>				
	At 1 kHz	3.3	—	—	—
IEC250	<b>Dissipation factor</b>				
	At 1 kHz	0.003	—	—	—
IEC93	<b>Volume resistivity (ohm-cm)</b>				
	At 23°C, 50% RH	4.9x10 <sup>16</sup>	—	—	1.4x10 <sup>5</sup>